

PRODUCT DATA SHEET DP I Emulsion Non-Fibered Damp Proofing

USES

AIM DP I Emulsion Non-Fibered Damp Proofing coating is ideal for reducing dampness and moisture infiltration through foundation walls, parapets, firewalls, tanks, culverts, cisterns, and bridge abutments. AIM DP I Emulsion Non-Fibered Damp Proofing is applicable for above-grade cavity wall applications and below-grade masonry wall damp proofing. The AIM damp proofing product line also helps to minimize internal structural damage from mildew and mold. Suitable for "green" or slightly damp surfaces.

DESCRIPTION

AIM DP I Emulsion Non-Fibered Damp Proofing is a cold-applied water-based asphalt emulsion damp proofing and vapor-retarding coating. Suitable for use on "green" or slightly damp surfaces. AIM DP I Emulsion Non-Fibered Damp Proofing is fiber-free for application by brush or spray.

APPLICATION

AIM DP I Emulsion Non-Fibered Damp Proofing should only be applied when temperatures are expected to remain above 50°F for the next 24 hours. Surface to be coated should be free of oil, grease, dirt, laitance and loose material. Dry surfaces must be dampened with water and kept damp until application. Apply AIM DP I Emulsion Non-Fibered Damp Proofing by brush, roller or spray with the proper equipment. Consult the spray equipment manufacturer for more information. For dense surfaces and exterior surfaces below grade: Fill in all crevices and grooves, making sure coating is continuous and free from breaks and pinholes. Carry coating over exposed top and outside edge of footing. Spread around all joints, grooves, and slots and into all chases, corners, reveals, and soffits. Bring the coating to finished grade. Backfilling should be done within 24 - 48 hours after application. Do not longer than seven days maximum before backfilling. Be careful not to damage or rupture the film or displace coating. Some situations may require protection board. Clean wet coating with soap and water. Dry coating may be removed with mineral spirits. Use care when handling solvents.

KEEP FROM FREEZING

CAUTION

Do not take internally. Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. If swallowed, do not induce vomiting.

KEEP OUT OF REACH OF CHILDREN.

First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water.

If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

Warning: This product contains a chemical known to the State of California to cause cancer.

SPECIFICATIONS

ASTM D 1187, Type I ASTM D 1227, Type III, Class 1 Coverage: Approximately 70 - 100 ft.²/gal. (1.71- 2.45 m²/L) per coat. Container sizes 5 Gallon (19 L) Pails 55 Gallon (208 L) Drums VOC < 50 g/l



LIMITED WARRANTY

TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of 12 months from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application.

LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

