



# PRODUCT DATA SHEET

## AIM DP VI Solvent Trowel Mastic

### USES

AIM DP VI Solvent Semi Mastic Damp Proofing is ideal for reducing dampness and moisture infiltration through foundation walls, parapets, firewalls, tanks, culverts, cisterns, and bridge abutments. AIM Solvent Trowel Mastic is applicable for above-grade cavity wall applications and below-grade masonry wall damp proofing. The AIM damp proofing product line also helps to minimize internal structural damage from mildew and mold. AIM Solvent Trowel Mastic can be used for below-grade damp proofing of walls and foundations. The product provides a continuous, vapor-resistant film; has an excellent bond to clean, cured concrete. AIM Solvent Trowel Mastic protects metal surfaces against corrosion. The material remains flexible and crack resistant under normal expansion and contraction.

### DESCRIPTION

AIM DP VI Solvent Trowel Mastic Damp Proofing is a cold-applied, solvent-based asphalt damp proofing and vapor-retarding coating. AIM Solvent Trowel Mastic is reinforced with long fibers for application by trowel. AIM DP VI Solvent Trowel Mastic is a heavy-bodied, fibered asphalt compound for the exterior surface of below-grade masonry wall surface applications. It is recommended to protect porous or irregular surfaces.

### APPLICATION

**SURFACE MUST BE COMPLETELY DRY AND FULLY CURED PRIOR TO APPLICATION.**

Do not apply AIM Solvent Trowel Mastic when temperatures below 35° F (2° C) are anticipated. Do not apply in rain or when rain is threatening. Surface to be coated should be free of oil, grease, dirt, laitance and loose material. Apply AIM Solvent Trowel Mastic by trowel. If primer is required, use AIM Solvent Spray Mastic.

AIM Solvent Trowel Mastic can be applied directly from the container.

### FOR DENSE EXTERIOR BELOW-GRADE SURFACES

Apply AIM Solvent Trowel Mastic by trowel. For dense surfaces and exterior surfaces below grade: Fill in all crevices and grooves, making sure coating is continuous and free from breaks and pinholes. Carry coating over exposed top and outside edge of footing. Spread around all joints, grooves, and slots and into all chases, corners, reveals, and soffits. Bring the coating to finished grade. Backfill should be done within 24 - 48 hours after application. Do not wait longer than seven days maximum before backfilling. Be careful not to damage or rupture the film or displace coating. Some situations may require protection board.

### FOR POROUS EXTERIOR BELOW-GRADE SURFACES: Three Options are available.

1. For Membrane System: For severe conditions or for added protection, apply one coat of AIM Solvent Trowel Mastic Damp Proofing on porous surfaces (such as block), according to Dense Exterior Below-Grade Surfaces Application, listed above. Within four hours, apply a glass fabric membrane cloth over all coating surfaces. Overlap all edges by 3" minimum. Press firmly into place without wrinkles. Application of the second coat of AIM Solvent Semi Mastic Damp Proofing should be within 24 hours.
2. For Two-Coat System: Apply AIM Solvent Spray Mastic Damp Proofing as a prime coat. Allow coat to dry tacky to touch, then apply AIM Solvent Trowel Mastic in one coat, according to Dense Exterior Below-Grade Surfaces Application, listed above. Backfill should be done within 24 - 48 hours after application. Do not wait longer than seven days maximum before backing. Be careful not to damage or rupture the film or displace coating. Some situations may require protection board.
3. For Parge Coat System: Before application of AIM Solvent Trowel Mastic Damp, apply a heavy parge coat of cement mortar for surface preparation. The coat should cover the bottom of the footing to grade level, forming a cove at the junction of the wall and footing. Once the parge coat cures, apply one coat of AIM Solvent Trowel Mastic Damp Proofing according to Dense Exterior Below-Grade Surfaces Application, listed above. Backfill should be done within 24 - 48 hours after application. Do not wait longer than seven days maximum before backfilling. Be careful not to damage or rupture the film or displace coating. Some situations may require protection board.

### FOR INTERIOR ABOVE-GRADE SURFACES-VAPOR RETARDER

AIM Solvent Trowel Mastic Damp Proofing can be used individually or in combination with AIM Solvent Spray-Mastic or AIM Solvent Semi Mastic for damp-proofing the exterior face of interior walls in cavity wall construction.

Clean up with mineral spirits or waterless hand cleaner. Use care when handling solvents.



**CAUTION**  
**COMBUSTIBLE LIQUID AND VAPOR**

Contains petroleum distillate. Harmful or fatal if swallowed.

Vapor harmful. May affect the brain or central nervous system causing dizziness, headache, or nausea. Causes nose and throat irritation. Causes eye irritation. Causes skin irritation. Reports have associated repeated and prolonged occupational exposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling contents may be harmful or fatal.

Keep away from heat and open flame. Use only with adequate ventilation. Do not breathe vapors. If you experience eye watering, headache, or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin, and clothing. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN.**

**First Aid:** In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting. Get medical attention immediately.

If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

**Warning:** This product contains a chemical known to the State of California to cause cancer.

**SPECIFICATIONS**

ASTM D 4586, Type 1

VOC 250 g/l

Exterior Below-Grade Dense Surfaces and Exterior Below- Grade  
Porous Surfaces:

1/16" wet film thickness: 20-25 sq.ft/gal; 1/8" wet film thickness:  
10-12.5 sq.ft/gal

Container sizes:  
5 Gallon (19 L) Pails  
55 Gallon (208 L) Drums

**LIMITED WARRANTY**

**TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.**

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of 12 months from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application.

**LIMITATION OF LIABILITY:** In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

